

# Liveo™ Q7-9120 Silicone Fluid 12500 cSt

### Silicone Topical Excipients

#### Excipient for pharmaceutical applications

Liveo<sup>™</sup> Q7-9120 Silicone Fluid is a clear, colorless polydimethylsiloxane liquid, available in a range of six narrow viscosities: 20 cSt, 100 cSt, 350 cSt, 500 cSt, 1,000 cSt and 12,500 cSt. Liveo<sup>™</sup> Q7-9120 Silicone Fluid is used to formulate with other organic and inorganic material for topical applications.

#### Composition:

Chemical name: Polydimethylsiloxane, INCI name: Dimethicone, CAS number: 63148-62-9

### Applications, Features & Benefits:

As an excipient (inactive ingredients), Liveo™ Q7-9120 Silicone Fluid in topical pharmaceutical applications, including dermatological treatments, can provide emolliency, ease of spreading, smooth feel, long lasting lubrication and reduced tackiness. Liveo™ Q7-9120 Silicone Fluid is currently used in a range of dermatological treatments and pharmaceutical applications such as creams, gels and sticks. As a skin protectant active ingredient in over-the-counter topical applications, Liveo™ Q7-9120 Silicone Fluid helps prevent and temporarily protects skin and lips against chafing, chapping, cracking and windburn in accordance with FDA guidelines. Clear, emollient, Non-occlusive, skin protectant, Water repellant, Smooth feel, spreadability, Lubricity

#### Packaging:

Liveo™ Q7-9120 Silicone Fluid is available in pails and in drums. Samples for Liveo™ Q7-9120 Silicone Fluid are available in bottles.

#### Product information

Colour Transparent -

Volatiles 0.17 % EN 1400 / EN 14350-2

Rheological properties

Viscosity 12100 mPa.s

Other properties

Refractive index 1.405

Storage and stability

Shelf life 60 months

Additional Information

How to use Liveo™ Q7-9120 Silicone Fluid is soluble in organic solvents such as aliphatic

and aromatic hydrocarbons. Liveo $^{\mathsf{TM}}$  Q7-9120 Silicone Fluid is compatible with a range of materials that make formulation relatively easy. Liveo $^{\mathsf{TM}}$  Q7-9120 Silicone Fluid can be used alone or blended with other silicone to provide a fluid base for a variety of formulations and provide a smooth, long lasting film on the skin. The fluid is easily emulsified in water with standard emulsifiers

Revised: 2020-09-11 Page: 1 of 3



## Liveo™ Q7-9120 Silicone Fluid 12500 cSt

### Silicone Topical Excipients

and normal emulsification techniques.

#### Blending:

Although the fluid is available in a number of standard viscosities, occasionally an application calls for a fluid of an intermediate viscosity. Blending of different viscosities of Liveo™ Q7-9120 Silicone Fluid permits any desired viscosity between 20 cSt and 12,500 cSt. The blending chart is a guideline for preparing intermediate fluid viscosities. Accuracy is obtained by blending the two fluids that immediately bracket the desired viscosity. If a very accurate blend is required, it may be necessary to adjust the viscosity of the mixture by a second blending.

The blending chart is a guideline for preparing intermediate fluid viscosities. To use the blending chart:

- 1. Draw a line between two points one on the left-hand scale representing the higher-viscosity fluid available, and one on the right, the lower-viscosity fluid;
- 2. Draw another line horizontally across the chart at the desired viscosity rating;
- 3. Draw a third line vertically through the intersection of the first two lines;
- 4. Read from the top and bottom scales the proportions of the available fluids to blend to obtain the desired viscosity.

Accuracy is increased by blending the two fluids that immediately bracket the desired viscosity. If a very accurate blend is required, it may be necessary to adjust the viscosity of the mixture by a second blending.

The example shown in the blending chart is as follows: 150 cSt fluid is desired. The standard viscosities immediately bracketing 150 cSt are 100 and 350 cSt. Draw line A connecting 350 cSt on the left-hand scale with 100 cSt on the right-hand scale. Draw line B horizontally at the desired viscosity of 150. At the point of intersection, AB, draw vertical line C. The proportion of 100 cSt viscosity fluid (67%) is read on the bottom scale; the proportion of 350 cSt viscosity fluid (33%) is read on the top scale.

#### Sterilization:

Steam Autoclaving: Sterilization of bulk fluid by steam autoclaving is not recommended. Excess water diffuses into the fluid, causing the fluid to become hazy. Dry Heat: Sterilization of bulk fluid is not recommended. Thin layers of fluid may be satisfactorily sterilized by this method. The temperature of the fluid should not exceed 150°C because of the potential for small amounts of formaldehyde to be generated. Gamma Irradiation: The exposure of polydimethylsiloxane fluids, such as Liveo™ Q7-9120 Silicone Fluid, to 25 kGy of cobalt-60 radiation has the effect of introducing small levels of cross-linking into the fluid and is observed as an increase in fluid viscosity. As with any

Revised: 2020-09-11 Page: 2 of 3



## Liveo™ Q7-9120 Silicone Fluid 12500 cSt

Silicone Topical Excipients

exposure of the product to radiation, product performance and stability should be evaluated after exposure to determine if such treatment has detrimental effects

Revised: 2020-09-11 Page: 3 of 3

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2020 DuPont. All rights reserved.